

MODELO / MODEL		ARTICWOOD SERIES		
FOTO / PICTURE (orientative)		 P.E. ARTICWOOD AMBER MT 23X120 RECT.	 P.E. ARTICWOOD ARGENT MT 23X120 RECT.	
		 P.E. ARTICWOOD CAMEL MT 23X120 RECT.	 P.E. ARTICWOOD ICE GRAY MT 23X120 RECT.	
		 P.E. ARTICWOOD MOCHA MT 23X120 RECT.		
FORMATO / SIZE		23 X 120 cms.		
GRUPO / GROUP		Bla		
TIPO / TYPE		PORCELANICO ESMALTADO / Glazed Porcelain Tile		
DESCRIPCION DEL TEST / TEST DESCRIPTION		VALOR DEL TEST / TEST VALUE		NORMA / STANDARD
ABSORCIÓN DE AGUA / WATER ABSORPTION		AA < 0,5%	Cumple / Passed	UNE-EN-ISO 10545-3
FUERZA DE ROTURA / BREAKING STRENGTH		> 1300 N	Cumple / Passed	UNE-EN-ISO 10545-4
RESISTENCIA A LA FLEXIÓN / RESISTANCE OF FLEXION		> 35 N/mm2	Cumple / Passed	UNE-EN-ISO 10545-4
ABRASION SUPERFICIAL / SURFACE ABRASION		Clase / Class	Mocha, Amber PEI III Rest PEI IV	UNE-EN-ISO 10545-7
RESISTENCIA AL CUARTEO / CRACKING RESISTANCE		Requerido / Requested	Cumple / Passed	UNE-EN-ISO 10545-11
RESISTENCIA A LA HELADA / FROST RESISTANCE		Requerido / Requested	Cumple / Passed	UNE-EN-ISO 10545-12
RESISTENCIA QUIMICA / CHEMICAL RESISTANCE	(PRODUCTOS DOMESTICOS Y DE PISCINA / Domestic & Swimming Pool Products)	Mínimo / Minimum GB	Cumple / Passed	UNE-EN-ISO 10545-13
RESISTENCIA A LOS ACIDOS / ACID RESISTANCE		GHA	Cumple / Passed	UNE-EN-ISO 10545-13
RESISTENCIA A LAS BASES / ALKALINE RESISTANCE		GHA	Cumple / Passed	UNE-EN-ISO 10545-13
RESISTENCIA A LAS MANCHAS / RESISTANCE TO STAINS		Mínimo / Minimum Class 3	Cumple / Passed	UNE-EN-ISO 10545-14
RESISTENCIA AL DESLIZAMIENTO / SLIP RESISTANCE		Metodo Disponible / Available Method	R9 (6°<R<10°)	DIN 51130:2014-5
RESISTENCIA AL RAYADO / HARDNESS (MOHS)		Mínimo / Minimum 3	Cumple / Passed	EN 101